

Water Vapour Transmission Test Certificate

Monday, May 30th 2016

Supplier: Nordic Built Australia (PO Box 3151, Brighton, VIC, 3186)

Sample Description: NBU2MB-SU702 – Nordic Built 2mm moisture barrier underlay

Date Tested: May 2016 (Tested by FORAY Laboratories)


Test Method: ASTM E96 “Standard Test Method for Water Vapor Transmission of Materials (water method) at 22.5±2°C and 48±5 %RH.”

Water Resistance Data:

| | |
|---|---------------------|
| Sample Name | NBU2MB-SU702 |
| Water Vapour Transmission (g/m²/day/mmHg) | 0.018 |
| Water vapour transmission rate (g/m²/hr) | 0.015 |
| Sd value (m) | 117 |



Dr. Vyt Garnys
PhD, BSc(Hons) AIMM, ARACI, ISIAQ
ACA, AIRAH, FMA
Managing Director and Principal Consultant



Tuan Duong
B.E Chem.
Consultant



Nick Joy
BSc (Hons)
Consultant

CV160532